TEST REPORT

WO:26-02-2313 Sr. No. 3M / 3 -X-Cr- Hold

ULR - TC772626000023345F

Customer's Name : ROSALEE COLOURS PRIVATE LIMITED-WAGHODIA
C1/137, GIDC, ESTATE, WAGHODIA-391760

Test Report No. : **128LZ-26/ 2026**
Date of Report : 31-03-2026
Date of Receipt : 16-02-2026

Particulars of Sample : PAINTED TEST PANELS WITH PROTECTED ANTI CORROSIVE PRIMER & PAINT

Identification of Sample : ROSATHANE CF 374 P.U. PAINT (PRIMER + M.I.O + PAINT 3 COAT):DFT 180-240 MICRONS.

128LZ-26 SALT SPRAY TEST **Date of Testing : 31-03-2026**

Test Method : As Per ASTM B-117: 2019 (With Photograph)

Test Condition	Standard Requirements	Observed Values	Remarks
Type of Salt Solution :	5% W/V of NaCl in Distilled Water	5% W/V	OK
Average pH of Atomized & Collected Solution :	6.5 – 7.2	6.84	OK
Temperature in Salt Spray Chamber :	35.0°C ± 2°C	34°C	OK
Average Fog Collection :	1 - 2 ml/hr	1.6 ml/hr	OK
Specific Gravity of Collected Solution at 25°C :	1.0242 - 1.0372 g/cm³	1.0300 g/cm³	OK
Angle of Sample Inclination :	15˚ to 25˚ (Vertical)	20˚	OK
Method of Supporting Sample in Test chamber :	Suspended using Nylon thread and placed at an angular seat.		
Description of Protection used :	White transparent tape used to cover the edges.		
Date and Time of Loading :	DT : 16/02/2026 Time : 05:00 P.M.		
Date and Time of Unloading :	DT : 30/03/2026 Time : 09:00 A.M.		
Total Exposure Time :	1000 hours		
Method of Cleaning Before Test :	Gently wiped with clean cotton to remove dust particles.		
Method of Cleaning After Test :	Gently washed in clean running water to remove salt deposits from surface and dried immediately.		
Visualization before test :	No Rust observed on test piece.		
Visualization after test :	After the continuous exposure for 1000 hours, no white rust is observed on the test piece. No Red rust is observed on the test piece.		

128LZ-26+1+6

A.M. Dave(QM)

Reviewed By **Authorized Signatory** **Witnessed By**

Continued on next page...

Reporting Conditions:
(1) Sample(s) not drawn by MHEPL. The results relate only to the sample(s) tested.
(2) This Certificate shall not be reproduced, except in full, without the written approval of MHEPL.
(3) If balance material is available after testing, it will be retained for 15 days maximum. If customer wants to retain it for one month from this date, he has to inform in written or he has to collect the same.
(4) While Met-Heat has made the best endeavors to provide accurate and reliable information, Met-Heat is not responsible for any financial liability due to act of omission or error made.(5) No Uncertainty of measurements accounted for decision rules for the reported conformity statement as per customer requirement. (6) The location of the performance : At Permanent facility

TEST REPORT

WO:26-02-2313 Sr. No. 3M / 3 -X-Cr- Hold

Test Report No.: 128LZ-26 / 2026

Date of Report : 31-03-2026
Date of Receipt : 16-02-2026

Sr. No.	Date	Time	Hours	Fog Collection (ml/hour)	pH
1	17-February-2026	05:00 P.M.	24 hours	1.5	6.85
2	18-February-2026	05:00 P.M.	48 hours	1.6	6.80
3	19-February-2026	05:00 P.M.	72 hours	1.6	6.92
4	20-February-2026	05:00 P.M.	96 hours	1.5	6.90
5	21-February-2026	05:00 P.M.	120 hours	1.7	6.60
6	22-February-2026	05:00 P.M.	144 hours	1.6	6.80
7	23-February-2026	05:00 P.M.	168 hours	1.6	6.80
8	24-February-2026	05:00 P.M.	192 hours	1.5	6.90
9	25-February-2026	05:00 P.M.	216 hours	1.7	6.90
10	26-February-2026	05:00 P.M.	240 hours	1.6	6.90
11	27-February-2026	05:00 P.M.	264 hours	1.8	6.80
12	28-February-2026	05:00 P.M.	288 hours	1.5	6.80
13	01-March-2026	05:00 P.M.	312 hours	1.5	6.80
14	02-March-2026	05:00 P.M.	336 hours	1.6	6.90
15	03-March-2026	05:00 P.M.	360 hours	1.5	6.90
16	04-March-2026	05:00 P.M.	384 hours	1.8	6.80
17	05-March-2026	05:00 P.M.	408 hours	1.8	6.90
18	06-March-2026	05:00 P.M.	432 hours	1.6	6.90
19	07-March-2026	05:00 P.M.	456 hours	1.6	6.80
20	08-March-2026	05:00 P.M.	480 hours	1.5	6.90
21	09-March-2026	05:00 P.M.	504 hours	1.5	6.90
22	10-March-2026	05:00 P.M.	528 hours	1.4	6.90
23	11-March-2026	05:00 P.M.	552 hours	1.5	6.80
24	12-March-2026	05:00 P.M.	576 hours	1.6	6.90
25	13-March-2026	05:00 P.M.	600 hours	1.7	6.80

Continued on next page...

A.M. Dave(QM)

Reviewed By **Authorized Signatory** **Witnessed By**

Continued on next page...

Reporting Conditions:
(1) Sample(s) not drawn by MHEPL. The results relate only to the sample(s) tested.
(2) This Certificate shall not be reproduced, except in full, without the written approval of MHEPL.
(3) If balance material is available after testing, it will be retained for 15 days maximum. If customer wants to retain it for one month from this date, he has to inform in written or he has to collect the same.
(4) While Met-Heat has made the best endeavors to provide accurate and reliable information, Met-Heat is not responsible for any financial liability due to act of omission or error made.(5) No Uncertainty of measurements accounted for decision rules for the reported conformity statement as per customer requirement. (6) The location of the performance : At Permanent facility

128LZ-26+2+6

TEST REPORT

WO:26-02-2313 Sr. No. 3M / 3 -X-Cr- Hold

Test Report No.: 128LZ-26 / 2026

Date of Report : 31-03-2026
Date of Receipt : 16-02-2026

Sr. No.	Date	Time	Hours	Fog Collection (ml/hour)	pH
26	14-March-2026	05:00 P.M.	624 hours	1.6	6.90
27	15-March-2026	05:00 P.M.	648 hours	1.5	6.80
28	16-March-2026	05:00 P.M.	672 hours	1.5	6.90
29	17-March-2026	05:00 P.M.	696 hours	1.6	6.90
30	18-March-2026	05:00 P.M.	720 hours	1.5	6.90
31	19-March-2026	05:00 P.M.	744 hours	1.5	6.80
32	20-March-2026	05:00 P.M.	768 hours	1.5	6.80
33	21-March-2026	05:00 P.M.	792 hours	1.6	6.80
34	22-March-2026	05:00 P.M.	816 hours	1.5	6.80
35	23-March-2026	05:00 P.M.	840 hours	1.5	6.80
36	24-March-2026	05:00 P.M.	864 hours	1.5	6.80
37	25-March-2026	05:00 P.M.	888 hours	1.6	6.80
38	26-March-2026	05:00 P.M.	912 hours	1.5	6.90
39	27-March-2026	05:00 P.M.	936 hours	1.6	6.80
40	28-March-2026	05:00 P.M.	960 hours	1.6	6.80
41	29-March-2026	05:00 P.M.	984 hours	1.5	6.90
42	30-March-2026	09:00 A.M.	1000 hours	1.6	6.80
Average				**1.6**	**6.84**

128LZ-26+3+6

A.M. Dave(QM)

Reviewed By **Authorized Signatory** **Witnessed By**

Continued on next page...

Reporting Conditions:
(1) Sample(s) not drawn by MHEPL. The results relate only to the sample(s) tested.
(2) This Certificate shall not be reproduced, except in full, without the written approval of MHEPL.
(3) If balance material is available after testing, it will be retained for 15 days maximum. If customer wants to retain it for one month from this date, he has to inform in written or he has to collect the same.
(4) While Met-Heat has made the best endeavors to provide accurate and reliable information, Met-Heat is not responsible for any financial liability due to act of omission or error made.(5) No Uncertainty of measurements accounted for decision rules for the reported conformity statement as per customer requirement. (6) The location of the performance : At Permanent facility

TEST REPORT

WO:26-02-2313 Sr. No. 3M / 3 -X-Cr- Hold

Test Report No.: 128LZ-26 / 2026

Date of Report : 31-03-2026
Date of Receipt : 16-02-2026

Sr. No.	Date	Time	Hours	Observation (White Rust, Red Rust)
1	17-February-2026	05:00 P.M.	24 hours	No rust observed.
2	18-February-2026	05:00 P.M.	48 hours	No rust observed.
3	19-February-2026	05:00 P.M.	72 hours	No rust observed.
4	20-February-2026	05:00 P.M.	96 hours	No rust observed.
5	21-February-2026	05:00 P.M.	120 hours	No rust observed.
6	22-February-2026	05:00 P.M.	144 hours	No rust observed.
7	23-February-2026	05:00 P.M.	168 hours	No rust observed.
8	24-February-2026	05:00 P.M.	192 hours	No rust observed.
9	25-February-2026	05:00 P.M.	216 hours	No rust observed.
10	26-February-2026	05:00 P.M.	240 hours	No rust observed.
11	27-February-2026	05:00 P.M.	264 hours	No rust observed.
12	28-February-2026	05:00 P.M.	288 hours	No rust observed.
13	01-March-2026	05:00 P.M.	312 hours	No rust observed.
14	02-March-2026	05:00 P.M.	336 hours	No rust observed.
15	03-March-2026	05:00 P.M.	360 hours	No rust observed.
16	04-March-2026	05:00 P.M.	384 hours	No rust observed.
17	05-March-2026	05:00 P.M.	408 hours	No rust observed.
18	06-March-2026	05:00 P.M.	432 hours	No rust observed.
19	07-March-2026	05:00 P.M.	456 hours	No rust observed.
20	08-March-2026	05:00 P.M.	480 hours	No rust observed.
21	09-March-2026	05:00 P.M.	504 hours	No rust observed.
22	10-March-2026	05:00 P.M.	528 hours	No rust observed.
23	11-March-2026	05:00 P.M.	552 hours	No rust observed.
24	12-March-2026	05:00 P.M.	576 hours	No rust observed.
25	13-March-2026	05:00 P.M.	600 hours	No rust observed.

Continued on next page...

A.M. Dave(QM)

Reviewed By **Authorized Signatory** **Witnessed By**

Continued on next page...

Reporting Conditions:
(1) Sample(s) not drawn by MHEPL. The results relate only to the sample(s) tested.
(2) This Certificate shall not be reproduced, except in full, without the written approval of MHEPL.
(3) If balance material is available after testing, it will be retained for 15 days maximum. If customer wants to retain it for one month from this date, he has to inform in written or he has to collect the same.
(4) While Met-Heat has made the best endeavors to provide accurate and reliable information, Met-Heat is not responsible for any financial liability due to act of omission or error made.(5) No Uncertainty of measurements accounted for decision rules for the reported conformity statement as per customer requirement. (6) The location of the performance : At Permanent facility

128LZ-26+4+6

TEST REPORT

WO:26-02-2313 Sr. No. 3M / 3 -X-Cr- Hold

Test Report No.: 128LZ-26 / 2026

Date of Report : 31-03-2026
Date of Receipt : 16-02-2026

Sr. No.	Date	Time	Hours	Observation (White Rust, Red Rust)
26	14-March-2026	05:00 P.M.	624 hours	No rust observed.
27	15-March-2026	05:00 P.M.	648 hours	No rust observed.
28	16-March-2026	05:00 P.M.	672 hours	No rust observed.
29	17-March-2026	05:00 P.M.	696 hours	No rust observed.
30	18-March-2026	05:00 P.M.	720 hours	No rust observed.
31	19-March-2026	05:00 P.M.	744 hours	No rust observed.
32	20-March-2026	05:00 P.M.	768 hours	No rust observed.
33	21-March-2026	05:00 P.M.	792 hours	No rust observed.
34	22-March-2026	05:00 P.M.	816 hours	No rust observed.
35	23-March-2026	05:00 P.M.	840 hours	No rust observed.
36	24-March-2026	05:00 P.M.	864 hours	No rust observed.
37	25-March-2026	05:00 P.M.	888 hours	No rust observed.
38	26-March-2026	05:00 P.M.	912 hours	No rust observed.
39	27-March-2026	05:00 P.M.	936 hours	No rust observed.
40	28-March-2026	05:00 P.M.	960 hours	No rust observed.
41	29-March-2026	05:00 P.M.	984 hours	No rust observed.
42	30-March-2026	09:00 A.M.	1000 hours	No rust observed.

128LZ-26+5+6

A.M. Dave(QM)

Reviewed By **Authorized Signatory** **Witnessed By**

Continued on next page...

Reporting Conditions:
(1) Sample(s) not drawn by MHEPL. The results relate only to the sample(s) tested.
(2) This Certificate shall not be reproduced, except in full, without the written approval of MHEPL.
(3) If balance material is available after testing, it will be retained for 15 days maximum. If customer wants to retain it for one month from this date, he has to inform in written or he has to collect the same.
(4) While Met-Heat has made the best endeavors to provide accurate and reliable information, Met-Heat is not responsible for any financial liability due to act of omission or error made.(5) No Uncertainty of measurements accounted for decision rules for the reported conformity statement as per customer requirement. (6) The location of the performance : At Permanent facility

TEST REPORT

WO:26-02-2313 Sr. No. 3M / 3 -X-Cr- Hold

Test Report No.: 128LZ-26 / 2026

Date of Report : 31-03-2026
Date of Receipt : 16-02-2026

PHOTOGRAPH BEFORE TEST



PHOTOGRAPH AFTER 1000 HOURS



----------End of Report----------

A.M. Dave(QM)

Reviewed By **Authorized Signatory** **Witnessed By**

Reporting Conditions:
(1) Sample(s) not drawn by MHEPL. The results relate only to the sample(s) tested.
(2) This Certificate shall not be reproduced, except in full, without the written approval of MHEPL.
(3) If balance material is available after testing, it will be retained for 15 days maximum. If customer wants to retain it for one month from this date, he has to inform in written or he has to collect the same.
(4) While Met-Heat has made the best endeavors to provide accurate and reliable information, Met-Heat is not responsible for any financial liability due to act of omission or error made.(5) No Uncertainty of measurements accounted for decision rules for the reported conformity statement as per customer requirement. (6) The location of the performance : At Permanent facility

128LZ-26+6+6